

MAESTRO® color

Matt woodfree tinted office paper.

The Hip-Hop dancer represents the different styles and possibilities of the impressive MAESTRO® color range. Subtle pastels, intense neon, pure black are just some highlights of the colours available. Whether you choose small or mixed packs, MAESTRO® color provides the ideal solution for your office communication needs – every time.

It has outstanding feeding properties and can be printed on both sides which makes it perfect for colour laser printing, inkjet printing and colour copies. Its even surface and high light-fastness guarantee the very highest quality.

Bright ideas need more than a white sheet of paper. Express your true colours with the MAESTRO® color collection.

MAESTRO® color is available in a range of 34 eye-catching, attention grabbing colours.



Certificates



Further certificates

FSC™, ISO 9706 Ageing Resistance, ISO 9001, ISO 14001, Green Range, ECF, ISO 45001, EN71-3 Toy Safety, REACH, Free of Heavy Metals, DIN 12281, OBA free Confirmation

Product benefits

Superb colour uniformity, surface structure and light fastness for excellent appearance

High environmental profile with dyes complying with EN 71-3 (European Standard for Safety of Toys)

Heavy metal absence 94/62/CE FSC™ certified

Fully biodegradable & recyclable

Multifunctional office paper – best print results with all print and copy machines, whether laser, inkjet or copy

Re-sealable transparent wrapper Available also in both mixed and small packs

This paper is optionally available as CO₂ neutral. Mondi is offsetting the unavoidable greenhouse gas emissions through certified carbon offset projects with ClimatePartner.

Typical applications

Flyers, Stationery, Training materials, Invoices, Greeting cards, Folders, Brochures

Technical specification | Intensive colours

Parameter Name	Unit	ISO code	80 ¹	80 ²	120 ³	120 ⁴	160 ⁵	160 ⁶
Basis weight	g/m ²	ISO 536	80 ± 3.0	80 ± 3.0	120 ± 5.0	120 ± 4.0	160 ± 6.0	160 ± 6.0
Caliper	µm	ISO 534	105 ± 4	96 ± 3	145 ± 5	159 ± 6	214 ± 6	194 ± 5
Roughness Bendtsen	ml/min	ISO 8791-2	230 ± 50			230 ± 50	230 ± 50	
Moisture abs.	%	ISO 287	4.8 ± 0.5	6.5 ± 0.5	6.5 ± 0.5	4.8 ± 0.5	4.8 ± 0.5	6.5 ± 0.5
Tensile Strength	kN/m	ISO 1924-2		4.5 ± 0	7.7 ± 1			9.3
Tensile Strength	kN/m	ISO 1924-2		2.8	4.4			5.1
Tear	mN	ISO 1974		480 ± 30	900 ± 100			1,350 ± 150
				500	910			1,400

Tear	mN	ISO 1974	± 30	± 100	± 150
Burst	kPa		210 ± 20	340 ± 70	430 ± 80

¹ A3,A4 | ² A4 | ³ A4 | ⁴ A4 | ⁵ A3,A4 | ⁶ A3,A4 |

SIGNIFICANCE OF VALUES: 2 SIGMA

Technical specification | Neon colours

Parameter Name	Unit	ISO code	80
Basis weight	g/m ²	ISO 536	80 ± 3.0
Caliper	µm	ISO 534	103 ± 4
Roughness Bendtsen	ml/min	ISO 8791-2	210 ± 50
Moisture abs.	%	ISO 287	4.8 ± 0.5
Tensile Strength	kN/m	ISO 1924-2	
Tensile Strength	kN/m	ISO 1924-2	
Tear	mN	ISO 1974	
Tear	mN	ISO 1974	
Burst	kPa		

SIGNIFICANCE OF VALUES: 2 SIGMA

Technical specification | Pale colours

Parameter Name	Unit	ISO code	80	120	160
Basis weight	g/m ²	ISO 536	80 ± 3.0	120 ± 4.0	160 ± 6.0
Caliper	µm	ISO 534	105 ± 4	159 ± 6	214 ± 6
Roughness Bendtsen	ml/min	ISO 8791-2	230 ± 50	230 ± 50	230 ± 50
Moisture abs.	%	ISO 287	4.8 ± 0.5	4.8 ± 0.5	4.8 ± 0.5
Tensile Strength	kN/m	ISO 1924-2			
Tensile Strength	kN/m	ISO 1924-2			
Tear	mN	ISO 1974			
Tear	mN	ISO 1974			
Burst	kPa				

SIGNIFICANCE OF VALUES: 2 SIGMA

Technical specification | Trend colours

Parameter Name	Unit	ISO code	80	120	160
Basis weight	g/m ²	ISO 536	80 ± 3.0	120 ± 5.0	160 ± 6.0
Caliper	µm	ISO 534	105 ± 4	159 ± 6	214 ± 6
Roughness Bendtsen	ml/min	ISO 8791-2	230 ± 50	230 ± 50	230 ± 50
Moisture abs.	%	ISO 287	4.8 ± 0.5	4.8 ± 0.5	4.8 ± 0.5
Tensile Strength	kN/m	ISO 1924-2			
Tensile Strength	kN/m	ISO 1924-2			
Tear	mN	ISO 1974			
Tear	mN	ISO 1974			
Burst	kPa				

SIGNIFICANCE OF VALUES: 2 SIGMA