

Munken Print White

Our aim with Munken Print White was to develop the ultimate book paper by combining the best properties of woodfree and wood-containing paper. Thus we have created a quality with bulk, strength, surface, readability and printability especially for book production. The result is a high quality white shaded book paper with a feel and stiffness suited to most types of books, for colour or black and white print. Munken Print White comes in a wide range of bulks and grammages in sheets and reels, enabling the same quality to be used for both covers and inserts. There is also a cream version: Munken Print Cream.

Munken Print White standard products are available as EU Ecolabel, FSC® – The mark of responsible forestry. www.fsc.org. FSC-C020637 and PEFC™ PEFC/05-33-99 certified.



The mark of
responsible forestry



Technical specifications

Basic information:	Optimized for text, Available in sheets, Available in reels
Surface:	Uncoated surface-sized
Shade:	White
Printing techniques:	Offset, Flexo, Laser (black/white), Inkjet (black/white)
Certificates/Statements:	FSC_C020637, PEFC_053399, EU Ecolabel, ECF, EMAS, ISO 14001, Paper Profile, Safety of Toys, Food contact, Cradle to Cradle Certified®

Munken Print White 15

Grammage (g/m²)	70	80	90	100	115	150	300 ^B
Opacity (%)	88	90	92	94	95	97	100
Thickness (µm)	105	120	135	150	172	225	450
Bulk (thickness/grammage)	1.5	1.5	1.5	1.5	1.5	1.5	1.5
Whiteness (CIE)	116	116	116	116	116	116	116
Brightness (ISO 2470/D65 %)	96	96	96	96	96	96	96
Roughness (Bendtsen, ml/min)	300	300	300	300	300	300	300

^B Laminated paper

Values are targets only and can be subject to changes over time without prior notice. You will find the latest technical information and other technical recommendations about our products at arcticpaper.com

Munken Print White 18

Grammage (g/m²)	70	80	90	100 ^D	115	150 ^D
Opacity (%)	88	90	92	94	95	97
Thickness (µm)	126	144	162	180	207	270
Bulk (thickness/grammage)	1.8	1.8	1.8	1.8	1.8	1.8
Whiteness (CIE)	116	116	116	116	116	116
Brightness (ISO 2470/D65 %)	96	96	96	96	96	96
Roughness (Bendtsen, ml/min)	500	500	500	500	500	500

^D Not standard production. Min. 10 tonnes and paper machine trim needed.

Values are targets only and can be subject to changes over time without prior notice. You will find the latest technical information and other technical recommendations about our products at arcticpaper.com

Munken Print White 20

Grammage (g/m²)	70 ^D	80	90	100 ^D
Opacity (%)	88	90	92	94
Thickness (µm)	140	160	180	200
Bulk (thickness/grammage)	2.0	2.0	2.0	2.0
Whiteness (CIE)	116	116	116	116
Brightness (ISO 2470/D65 %)	96	96	96	96
Roughness (Bendtsen, ml/min)	1200	1200	1200	1200

^D Not standard production. Min. 10 tonnes and paper machine trim needed.

Values are targets only and can be subject to changes over time without prior notice. You will find the latest technical information and other technical recommendations about our products at arcticpaper.com